

ITEM - AGGREGATE SUBBASE (Class 6)

The Aggregate Subbase shall be Class 6, and shall be as specified in Section 303 of the Standard Specifications. The grading shall be as follows:

Sieve Size	% Passing

The plasticity index shall not exceed .

The estimated haul distance for the Aggregate Subbase is * miles.

DESIGNER:

This Item is used for Aggregate Subbase Class 6. The gradation and plasticity index requirements shown below are typical for Aggregate Subbase Class 6 and can be used as a guideline:

Sieve Size	% Passing
3"	100
1/4"	45 - 75
#200	0 - 15.0

The Plasticity Index shall not exceed 5.

* To be supplied by the Geotechnical Site Supervisor.

If the use of salvaged asphaltic concrete or Portland cement concrete is being considered for Aggregate Subbase on a project, see Item # 303a.