Lab Name: *Approved Testing Lab Inc.*

Type of Report: Asphalt Report Format Sample

Client: General Contractors, Inc.
Project Name: Rt 66 widening
Project Location: Phoenix
Material Type: asphalt
Material Source: Asphalt R US

ATLI Job No.: 2547JTT306
ADOT Tracs No.: H4473021C
Report Date: August 10, 2008
Technician: Bill Swanson

						Gradation Size														Required Tests														
ID	Date	Location	Time	Avg % AC	Tons	1"	3/4"	1/2"	3/8"	1/4"	#4	#8	#10	#16	#30	#40	#50	#100	#200	Moisture Content	Gradation	Sand Equivalent	Frac. Course Agg Particles	Uncompacted Void	Flakiness Index	Corr AC	% Asphalt	% Asphalt Rubber	Moisture Content	Gradation	Marshall	Rice	Compaction	Gyratory Density	Air Voids
1	8/4/08	Lot 11-1, Southbound travel lane bottom lift	9:30 PM			100	98	81	73	64	59	43	39	29	20	15	11	6	4							5.3					151.4	160.1			5.4
2	8/5/08	Lot 11-2, Southbound travel lane bottom lift, Sta 65+00	12:05 AM			100	96	78	68	56	52	39	35	26	17	13	10	5	3.1							5.9					152.8	157.3			2.9
3	8/6/08	Lot 11-3, Top lift Sta 63+50	8:55 PM			100	99	81	72	60	55	40	37	27	18	14	10	5	3.4							5.1					150.3	159.6			5.8
4	8/7/08	Lot 12-1, Southbound travel lane, bottom lift	12:01 AM			100	99	80	69	59	54	38	35	26	17	13	10	5	3.2							5.1					150.2	159.6			5.9
5	8/7/08	Lot 12-1, Southbound travel lane, top lift, 40+00	1:20 AM			100	99	80	69	60	55	39	35	26	17	13	10	5	3.4							5.1					151.8	161.1			5.8