

Lab Name: Approved Testing Lab Inc.

Type of Report: \_\_\_\_\_ Cold Feed

<p>Client: <u>General Contractors</u></p> <p>Project Name: <u>Route 66</u></p> <p>Project Location: <u>Phoenix</u></p> <p>Material Type: _____</p> <p>Material Source: _____</p>	<p>ATLI Job No.: <u>0180841ZA</u></p> <p>ADOT Tracs No.: <u>STP-069-A(203)A</u></p> <p>Report Date: <u>August 8, 2008</u></p> <p>Technician: <u>Bill Swanson</u></p>
--	--

ID	Date	Location	Time	Tons	Gradation Size														Mineral Aggregate					HMA																		
					1"	3/4"	1/2"	3/8"	1/4"	#4	#8	#10	#16	#30	#40	#50	#100	#200	Moisture Content	Sand Equivalent	Frac. Course Agg Particles	Uncompacted Void	Flakiness Index	% Asphalt	% Asphalt Rubber	Moisture Content	Coorect Asphalt Binder Content	Marshall	Rice	Compaction	Gyratory Density	Air Voids										
1	8/4/08	Hot Plant	11:15 AM	665	100	99	85	74	65	61	45	42	31	21	16	12	6	4.1	66.0		45.2																					
2	8/7/08	Hot Plant	8:30 PM	100	100	99	80	74	59	54	40	36	27	18	14	10	5	2.8	N/A		45.4																					