Lab Name: ***Approved Testing Lab, Inc*** **Type of Report:** **Concrete Format Sample**

Client: General Contactors Inc
Project Name: Route 66
Project Location: Phoenix
Material Type:
Material Source: Concrete R Us

ATLI Job No.: 602039002
ADOT Tracs No.: H660109C
Report Date: November 17, 2008
Technician:

ID	Required Strength psi @ ___ days	Structure / Location	Supplier	Mix Code	Truck #	Ticket #	Load Volume ___ Cubic Yard	Cum Volume ___ Cubic Yard	Water Added	Concrete Temp	Cast By	Cast Time (Military Time)	Air Content	Unit Weight	Slump	Specimen Number	Specimen Type	Cured In	Date Tested	Age at Test Days	Ave Diameter (Inches)	Ave Cross Sectional Area (IN2)	Max Load	Compressive Strength PSI	Failure Type
1	4000	Abutment#2. Bottom 1/4	A,P, & S	P4025051	40	4002	10	10	0	78	SDG	11:00	4.1%	n/a	3.50	A	Cylinder	Lab	39756	4	4	12.57	50154	3990	D
2	4000	Abutment#2. Bottom 1/4	A,P, & S	P4025051	40	4002	10	10	0	78	SDG	11:00	4.1%	n/a	3.50	B	Cylinder	Lab	39759	7	4	12.57			
3	4000	Abutment#2. Bottom 1/4	A,P, & S	P4025051	40	4002	10	10	0	78	SDG	11:00	4.1%	n/a	3.50	C	Cylinder	Lab		Hold	4	12.57			
4	4000	Abutment#2. Bottom 1/4	A,P, & S	P4025051	40	4002	10	10	0	78	SDG	11:00	4.1%	n/a	3.50	D	Cylinder	Lab		Hold	4	12.57			