Lab Name: ***Approved Testing Lab***

Type of Report: **Friction Course Format Sample**

Client: General Contractors, Inc.
Project Name: Route 66
Project Location: Phoenix
Material Type:
Material Source: Ashpalt R Us

ATLI Job No.: 2547JTT306
ADOT Tracs No.: H4473021C
Report Date: August 10, 2008
Technician:

					Gradation Size														Mineral Aggregate					HMA								
ID	Date	Location	Time	Tons	1"	3/4"	1/2"	3/8"	1/4"	#4	#8	#10	#16	#30	#40	#50	#100	#200	Moisture Content	Sand Equivalent	Frac. Course Agg Particles	Uncompacted Void	Flakiness Index	% Asphalt	% Asphalt Rubber	Moisture Content	Coorect Asphalt Binder Content	Marshall	Rice	Compaction	Gyratory Density	Air Voids
1	8/26/08		8:30 PM			100				53	9							0.7														
2	8/26/08		11:30 PM			100				43	6							0.6														
3	8/26/08		2:00 AM			100				42	6							0.7														
4	8/26/08		3:00 AM			100				42	6							0.8														
5	8/27/08		7:30 PM			100				42	5							0.8														
6	8/27/08		9:30 PM			100				46	9							0.9														
7	8/27/08		11:30 PM			100				45	5							0.6														
8	8/27/08		1:30 AM			100				50	6							1														
9	8/27/08		5:30 AM			n/a				n/a	n/a							n/a														
10	8/28/08		n/a			100				41	6							1														
11	8/28/08		n/a			100				51	12							1.3														
12	8/28/08		n/a			100				50	7							1.1														
13	8/28/08		n/a			n/a				n/a	n/a							n/a														